



Decorative & Architectural

Technical Data Sheet

D304-STD (Rev 1/2021)

PRODUCT NAME: ANTICORROSIVE ROOF PAINT

Generic Type: Long oil modified alkyd.

General Description

Especially formulated for use on metal roofing to withstand tropical weathering and to inhibit corrosion.

Recommended Uses:

- Galvanized iron
- Alu-zinc roofings
- Aluminium

Features/Benefits

- Tough finish
- Anti - fungus and mildew
- Glossy finish
- Anti - mildew
- Can be applied to appropriately primed metal roof
- Contains zinc rust inhibitors

Product Data:

No. of coats: 2

Spreading Rate:

8 - 10 m² per 0.95 litre depending on porosity of the surface.

Drying Time:

Touch Dry: 4 - 6 hrs.

Re - Coat: 16 - 18 hrs.

Hard Dry overnight

Application:

Brush, roller or spray.

Thin up to 10% (370 ml) p. 3.8 litres for spraying.

Gloss: Semi-Gloss

Colour:

Roof Red, Roof Green, Buckingham Green

Thinner/Cleaner:

Brush Kaleidoscope Thinner 2000

Roller Kaleidoscope Thinner 2000

Spray Kaleidoscope Thinner 2003

Flash Point:

39°C (102°F)



A Member of: kpl group

Head Office (868) 638-2213/6
Chanka Trace, El Socorro Ext. Rd
San Juan, Trinidad, W.I.

South Branch (868) 658-1818
#99 Market Street, Marabella,
Trinidad, W.I.

©2021 Kaleidoscope Paints Ltd • info@kplgroup.com • www.kscopaints.com

ISO 9001 DOC Control #KPL-QD-19/REV 01-1 TDS Revision #1/2021



Decorative & Architectural

Technical Data Sheet

D304-STD (Rev 1/2021)

PRODUCT NAME: **ANTICORROSIVE ROOF PAINT**

General Surface Preparation

NEW galvanize steel and aluminium surfaces should first be etched with Kaleidoscope Etching Wash Primer followed by one coat of Kaleidoscope Zinc Chromate Primer. Then apply 1 coat of Kaleidoscope Anti-Corrosive Roof Paint 16 – 18 hrs, after priming. Second coat should be applied 16-18 hrs, after the first coat is applied.

PREVIOUSLY painted surfaces should be thoroughly cleaned to remove any accumulation of dirt, grease or flaking material. Rusted areas should be replaced or treated with Kaleidoscope Rust Converter and spot primed with Kaleidoscope Zinc Chromate Primer and allowed to dry for 16 – 18 hrs, before applying. Then apply one or two coats of Kaleidoscope Anti-Corrosive Roof Paint.

For spraying thin with 470ml of Kaleidoscope 2000 Thinners per 3.785 liters.

NB: Always stir thoroughly before use and do not allow more than 18hrs drying between coats. Read label prior to use.

CAUTION: Use only with adequate ventilation. If you experience eye watering, headaches, or dizziness, increase fresh air or wear an approved particulate respirator (Follow respirator manufacturer's direction for respirator use) or leave the area. **Avoid contact with eyes.** Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage.

FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. **If swallowed, get medical attention immediately.**



A Member of:  **kplgroup**

Head Office (868) 638-2213/6
Chanka Trace, El Socorro Ext. Rd
San Juan, Trinidad, W.I.

South Branch (868) 658-1818
#99 Market Street, Marabella,
Trinidad, W.I.

©2021 Kaleidoscope Paints Ltd • info@kplgroup.com • www.kscopaints.com

ISO 9001 DOC Control #KPL-QD-19/REV 01-1 TDS Revision #1/2021