



Decorative & Architectural

Technical Data Sheet

1110-STD (Rev 1/2021)

PRODUCT NAME: QUICK DRYING SPRAY ENAMEL

Generic Type: Oil modified alkyd.

General Description:

A fast drying single - coat high gloss finish providing good gloss retention and abrasion resistance.

Recommended Uses:

For L.P.G. Cylinders.

Features/Benefits:

Quick Drying

Directions for Use:

Product Data:

No of Coats: 1 or 2

Solids Volume: 48%

Film Thickness: (per coat)

Wet 83 microns (3 mils)

Dry 40 microns (1 ½ mil)

Coverage: (per coat)

7-9 sq. m. @ 40 microns d.f.t.

75-100 sq.ft. @ 1 ½ mils. d.f.t

Drying Time:

Touch Dry 15-20 mins

Re-coat 4 hrs

Application: Brush or Spray

Gloss: High Gloss

Colour Range: Red, Grey, Yellow

Thinner / Cleaner:

Kaleidoscope Thiinner 2003

Flash Point: 23°C (73°F)

SURFACE PREPARATION:

Remove any dust, dirt, oil, grease, ooze and semi - adherent paintwork, rust millscale and other debris to obtain a clean dry sound surface. Clean to Hand Tool finish, SSPC-SP-2 or Power Tool Finish, SSPC-SP-3

APPLICATION: Apply 1 full coat Kaleidoscope Quick Drying Spraying Enamel.

CAUTION: Avoid contact with eyes. Keep container closed when not in use. Do not transfer contents to other containers for storage.

FIRST AID: in case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. **If swallowed, get medical attention immediately.**



A Member of: kplgroup

Head Office (868) 638-2213/6
Chanka Trace, El Socorro Ext. Rd
San Juan, Trinidad, W.I.

South Branch (868) 658-1818
#99 Market Street, Marabella,
Trinidad, W.I.

©2021 Kaleidoscope Paints Ltd • info@kplgroup.com • www.kscopaints.com
ISO 9001 DOC Control #KPL-QD-19/REV 01-1 TDS Revision #1/2021